

# YUMA INDUSTRIES

## YUMAX RUST PREVENTATIVES

YUMAX	APPEARANCE	SPECIFIC GRAVITY	VISCOSITY 40C/100F	FLASH C / F	FILM (MICRON)	FILM PROPERTIES	PROTECTION			BARIUM	REMOVABILITY	CHARACTERISTICS
							MOS.	SST	HCT			
WRS-10	LIGHT YELLOW LIQUID	0.79	1.6 / <32	74 / 165						NO		WATER DISPLACING AGENT-USED STRAIGHT-USED AFTER GRINDING & CLEANING OPERATIONS WHERE WATER AND OIL SEPARATION IS NEEDED.
WRS-50	LIGHT BRN LIQ.	0.80	2.1 / 33	57 / 135						NO		CONCENTRATE VERSION OF WRS-10. CAN VARY THE SOLUTION STRENGTH, DEPENDING ON THE AMOUNT OF WATER PRESENCE.
P-307	DRK BRN LIQ	0.88	4.4 / 41	42 / 108	6-7	OILY	6	72	>1000	YES	G / SOL G / ALK	STAIN FREE-OXIDATION RESISTANT-WATER DISPLACING-PARTICULARLY EFFECTIVE FOR PRECISION BEARINGS.
P-307BF	DRK BRN LIQ	0.87	4.4 /	42 / 108	6-7	OILY	6	72	>1000	NO	G / SOL G / ALK	NON STAINING-EXCELLENT CORROSION PROTECTION EXCEEDING 6 MONTHS-EXCELLENT WATER DISPLACING CHARACTERISTICS.
P-307D	LIGHT BRN LIQ.	0.80	2.2	80 /	1.1	OILY	1	8	500	YES	G / SOL G / ALK	UP TO 1 MONTH RUST PROTECTION. REDUCED FILM THICKNESS VERSION OF P-307N.
P-307H	LIGHT BRN LIQ.	0.83	3.3 / 36	76 / 169	2-4	OILY	4	24	1000	NO	G / ALK.	NON STAINING-EXCELLENT CORROSION PROTECTION FOR UP TO 6 MONTHS INDOOR AND PROTECTED OUTDOOR STORAGE.
P-307HF	LIGHT BRN LIQ	0.82	3.4 / 37	80 / 176	2-4	OILY	4	24	1000	NO	G / ALK.	HIGH FLASH POINT WITH EXCELLENT WATER DISPLACING PROPERTIES. EXCELLENT FOR UP TO 4 MONTHS INDOOR RUST PROTECTION.
P-307N	LIGHT BRN LIQ	0.83	3.3 / 37	70 / 178	2-4	OILY	4	24	1000	NO	G / ALK.	NON STAINING-EXCELLENT CORROSION PROTECTION FOR UP TO 1 YEAR INDOOR/PROTECTED OUTDOOR STORAGE. HIGH FLASH POINT.
P-310	DRK BRN LIQ	0.85	7.4 /	98 / 208	3-5	OILY	5	48	>1000	NO	G / ALK	UP TO 6 MONTHS INDOOR STORAGE PROTECTION. EXCELLENT FOR IN-PROCESS STEEL OR BEARING CORROSION PROTECTION.
P-329	BRN SUSPEN.	0.84	6.8 /	42 / 107	8-11	SL. WAXY	>6	>100	>1000	YES	G / SOL G / ALK	EXCELLENT FOR 6 OR MORE MONTHS INDOOR RUST PROTECTION. WATER DISPLACING.
P-352	LIGHT BRN LIQ	0.81	2.7 / 35	76 / 169	1-2	OILY	1	<8	750	YES	G / ALK.	UP TO 1 MONTH INDOOR STORAGE PROTECTION. EXCELLENT FOR COPPER PROTECTION. WATER DISPLACING-NON STAINING.
P-352BF	LIGHT BRN LIQ	0.82	2.9 / 35	77 / 171	1-2	OILY	1	<8	750	NO	G / ALK.	BARIUM FREE-UP TO 1 MONTH INDOOR STORAGE PROTECTION. SAME PROPERTIES AS P-352.
P-356	LIGHT BRN LIQ	0.80	2.1 / 33	76 / 169	1-2	OILY	1	<8	500	YES	G / ALK.	EXCELLENT RUST PROTECTION FOR UP TO 1 MONTH. DESIGNED FOR FERROUS METAL APPLICATIONS ONLY.
P-356BF	LIGHT BRN LIQ	0.80	2.1 / 33	76 / 169	1-2	OILY	1	<8	500	NO	G / ALK.	UP TO 1 MONTH INDOOR STORAGE PROTECTION-STAIN FREE-SAME PROPERTIES AS P-352.
P-901	LIGHT BRN LIQ	0.88	14.8 / 77	142/288	1-2	OILY	1			NO	G / ALK.	UP TO 3 MONTHS INDOOR PROTECTION. OIL BASED RUST PREVENT. HIGH FLASH POINT WITH EXCELLENT WATER DISPLACING PROPERTIES.
P-903	LIGHT BRN LIQ	0.88	8.0 /	150/302	1-3	OILY	1	<8	750	YES	G / ALK.	HIGH FLASH POINT WITH EXCELLENT WATER DISPLACING PROPERTIES. UP TO 3 MONTHS INDOOR PROTECTION. OIL BASED RUST PREVENT.
P-914	LIGHT BRN LIQ	0.88	10.0 /	176/348	1-3	OILY	1	<8	500	NO	G / ALK.	UP TO 4 MONTHS INDOOR RUST PROTECTION. HIGH FLASH POINT. RUST PREVENT WITH WATER DISPLACING PROPERTIES.
P-918	LIGHT BRN LIQ	0.86	11.5	176	1-3	OILY	1	<8	500	YES	G / ALK	UP TO 1 MONTH RUST PROTECTION. GOOD FOR STEEL COIL STOCK.
PSW-50	LIGHT BRN LIQ	0.92		N/A	1-3@20%	SL. OILY	3	<8	500	NO	G / ALK	WATER SOLUBLE OIL RP. EXCELLENT FOR DIP OR SPRAY APPLICATIONS.
PZ-2	LIGHT BRN LIQ	0.88	10.3 /	155/311	1-3	OILY	3	8	1000	YES	G / ALK	UP TO 3 MONTHS RUST PROTECTION ON ZINC COATED COIL STOCK.

